NCC LIMITED

WHITE TOPPING YELAHANKA FROM SHESHADRIPURAM FIRST GRADE COLLEGE TO AROMA BAKERY JUNCTION VAI 3RD CROSS ROAD, 1ST A MAIN ROAD, 16TH B CROSS ROAD

CONCRETE CUBES COMPRESSIVE STRENGTH TEST REPORT

Location : Dairy circle Junction To chikkabommasandra. Junction.

Chainage : 1678 TO 1739

Grade of Concrete : M40

DATE OF CASTING : 23/05/2022

DATE OF TESTING : 30/05/2022

DATE OF TESTING : 20/6/2022

Compressive strength test on concrete cubes specimens has been tested as per the guidelines of IS 516 /Part 1-2021 and the results are Tabulated below.

Sl.No	Quantity in 'Cum'	Samples of Cubes NO's	7 Days				28 Days				Remarks
			Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	
01	77.5	6	8.28	816	36.27	37.76	8.52	1269	56.4	56.37	
			8.42	862	38.31		8.68	1195	53.11		
			8.46	871	38.71		8.40	1341	59.60		

AGENCY PMC BBMP AGENCY PMC BBMP

NCC LIMITED

WHITE TOPPING YELAHANKA FROM SHESHADRIPURAM FIRST GRADE COLLEGE TO AROMA BAKERY JUNCTION VAI 3RD CROSS ROAD, 1ST A MAIN ROAD, 16TH B CROSS ROAD

CONCRETE CUBES COMPRESSIVE STRENGTH TEST REPORT

Location : Dairy circle Junction To chikkabommasandra Junction.

Chainage : 1739 To 1759

Grade of Concrete : M40

DATE OF CASTING : 24/05/2022

DATE OF TESTING : 01/06/2022

DATE OF TESTING : 21/06/2022

Compressive strength test on concrete cubes specimens has been tested as per the guidelines of IS 516 /Part 1-2021 and the results are Tabulated below.

Sl.No	Quantity in 'Cum'	Samples of Cubes NO's	7 Days				28 Days				Remarks
			Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	
01	26	6	8.38	773	34.36	35.7	8.56	1235	54.0	50.33	
			8.33	784	34.76		8.65	1055	46.8		
			8.30	854	38.0		8.42	1128	50.13		

AGENCY PMC BBMP AGENCY PMC BBMP

NCC LIMITED

WHITE TOPPING YELAHANKA FROM SHESHADRIPURAM FIRST GRADE COLLEGE TO AROMA BAKERY JUNCTION VAI 3RD CROSS ROAD, 1ST A MAIN ROAD, 16TH B CROSS ROAD

CONCRETE CUBES COMPRESSIVE STRENGTH TEST REPORT

Location : Dairy Circle to Chikkabommasandra Junction

Chainage : 1759 To 1814

Grade of Concrete : M40

DATE OF CASTING : 25/05/2022

DATE OF TESTING : 02/05/2022

DATE OF TESTING : 22/06/2022.

Compressive strength test on concrete cubes specimens has been tested as per the guidelines of IS 516 /Part 1-2021 and the results are Tabulated below.

Sl.No	Quantity in 'Cum'	Samples of Cubes NO's	7 Days				28 Days				Remarks
			Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	
01	71	6	8.45	892	39.64	39.21	8.43	1146	50.93	53.46	
			8.37	921	40.93		8.50	1188	52.86		
			8.28	834	37.07		8.60	1275	56.66		

AGENCY PMC BBMP AGENCY PMC BBMP

NCC LIMITED

WHITE TOPPING YELAHANKA FROM SHESHADRIPURAM FIRST GRADE COLLEGE TO AROMA BAKERY JUNCTION VAI 3RD CROSS ROAD, 1ST A MAIN ROAD, 16TH B CROSS ROAD

CONCRETE CUBES COMPRESSIVE STRENGTH TEST REPORT

Location : Dairy circle Junction to chikkabommasandra Junction.

Chainage : 1814 To 1862

Grade of Concrete : M40

DATE OF CASTING : 02/06/2022

DATE OF TESTING : 09/06/2022

DATE OF TESTING : 30/06/2022

Compressive strength test on concrete cubes specimens has been tested as per the guidelines of IS 516 /Part 1-2021 and the results are Tabulated below.

Sl.No	Quantity in 'Cum'	Samples of Cubes NO's	7 Days				28 Days				Remarks
			Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	
01	62.5	6	8.24	911	40.49	38.30	8.35	1325	58.88	56.27	
			8.39	830	36.89		8.50	1250	55.55		
			8.50	844	37.51		8.44	1224	54.40		

AGENCY PMC BBMP AGENCY PMC BBMP

NCC LIMITED

WHITE TOPPING YELAHANKA FROM SHESHADRIPURAM FIRST GRADE COLLEGE TO AROMA BAKERY JUNCTION VAI 3RD CROSS ROAD, 1ST A MAIN ROAD, 16TH B CROSS ROAD

CONCRETE CUBES COMPRESSIVE STRENGTH TEST REPORT

Location : Dairy circle Junction to chikkabommasandra Junction

Chainage : 1862 To 1892

Grade of Concrete : M40

DATE OF CASTING : 07/06/2022

DATE OF TESTING : 14/06/2022

DATE OF TESTING : 05/07/2022

Compressive strength test on concrete cubes specimens has been tested as per the guidelines of IS 516 /Part 1-2021 and the results are Tabulated below.

Sl.No	Quantity in 'Cum'	Samples of Cubes NO's	7 Days				28 Days				Remarks
			Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	
01	48	6	8.41	922	40.98	39.10	8.33	1041	46.26	51.16	
			8.34	881	39.16		8.36	1198	53.24		
			8.36	836	37.16		8.61	1215	54.0		

AGENCY PMC BBMP AGENCY PMC BBMP

NCC LIMITED

WHITE TOPPING YELAHANKA FROM SHESHADRIPURAM FIRST GRADE COLLEGE TO AROMA BAKERY JUNCTION VAI 3RD CROSS ROAD, 1ST A MAIN ROAD, 16TH B CROSS ROAD

CONCRETE CUBES COMPRESSIVE STRENGTH TEST REPORT

Location : Dairy circle Junction to chikkabommasandra Junction.

Chainage : 1862 To 1892

Grade of Concrete : M40

DATE OF CASTING : 07/06/2022

DATE OF TESTING : 14/06/2022

DATE OF TESTING : 05/07/2022

Compressive strength test on concrete cubes specimens has been tested as per the guidelines of IS 516 /Part 1-2021 and the results are Tabulated below.

Sl.No	Quantity in 'Cum'	Samples of Cubes NO's	7 Days				28 Days				Remarks
			Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	
01	48	6	8.41	922	40.98	39.10	8.33	1041	46.26	51.16	
			8.34	881	39.16		8.36	1198	53.24		
			8.36	836	37.16		8.61	1215	54.0		

AGENCY PMC BBMP

AGENCY PMC BBMP

NCC LIMITED

WHITE TOPPING YELAHANKA FROM SHESHADRIPURAM FIRST GRADE COLLEGE TO AROMA BAKERY JUNCTION VAI 3RD CROSS ROAD, 1ST A MAIN ROAD, 16TH B CROSS ROAD

CONCRETE CUBES COMPRESSIVE STRENGTH TEST REPORT

Location : Dairy circle Junction to chikkabommasandra Junction.

Chainage : 1892 To 1952

Grade of Concrete : M40

DATE OF CASTING : 08/06/2022

DATE OF TESTING : 15/06/2022

DATE OF TESTING : 06/07/2022

Compressive strength test on concrete cubes specimens has been tested as per the guidelines of IS 516 /Part 1-2021 and the results are Tabulated below.

Sl.No	Quantity in 'Cum'	Samples of Cubes NO's	7 Days				28 Days				Remarks
			Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	
01	96	6	8.21	945	42.0	40.48	8.51	1238	55.02	52.78	
			8.25	914	40.62		8.61	1230	54.66		
			8.19	874	38.84		8.35	1095	48.66		

AGENCY PMC BBMP AGENCY PMC BBMP

NCC LIMITED

WHITE TOPPING YELAHANKA FROM SHESHADRIPURAM FIRST GRADE COLLEGE TO AROMA BAKERY JUNCTION VAI 3RD CROSS ROAD, 1ST A MAIN ROAD, 16TH B CROSS ROAD

CONCRETE CUBES COMPRESSIVE STRENGTH TEST REPORT

Location : Dairy circle Junction to chikkabommasandra Junction

Chainage : 1952 TO 1967

Grade of Concrete : M40

DATE OF CASTING : 09/06/2022

DATE OF TESTING : 16/06/2022

DATE OF TESTING : 07/07/2022

Compressive strength test on concrete cubes specimens has been tested as per the guidelines of IS 516 /Part 1-2021 and the results are Tabulated below.

Sl.No	Quantity in 'Cum'	Samples of Cubes NO's	7 Days				28 Days				Remarks
			Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	
01	78	6	8.30	794	35.29	37.10	8.44	1237	54.97	56.04	
			8.42	891	39.6		8.54	1290	57.33		
			8.48	813	36.13		8.30	1257	55.86		

AGENCY PMC BBMP AGENCY PMC BBMP

NCC LIMITED

WHITE TOPPING YELAHANKA FROM SHESHADRIPURAM FIRST GRADE COLLEGE TO AROMA BAKERY JUNCTION VAI 3RD CROSS ROAD, 1ST A MAIN ROAD, 16TH B CROSS ROAD

CONCRETE CUBES COMPRESSIVE STRENGTH TEST REPORT

Location : Dairy Circle Junction to chikkabommasandra. Junction.

Chainage : 1967 TO 1980

Grade of Concrete : M40

DATE OF CASTING : 10/06/2022

DATE OF TESTING : 17/06/2022

DATE OF TESTING : 08/07/2022.

Compressive strength test on concrete cubes specimens has been tested as per the guidelines of IS 516 /Part 1-2021 and the results are Tabulated below.

Sl.No	Quantity in 'Cum'	Samples of Cubes NO's	7 Days				28 Days				Remarks
			Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	
01	76.5	6	8.37	826	36.71	38.13	8.41	1255	55.78	51.48	
			8.33	858	38.13		8.45	1036	46.04		
			8.31	890	39.56		8.36	1184	52.62		

AGENCY PMC BBMP

AGENCY PMC BBMP

NCC LIMITED

WHITE TOPPING YELAHANKA FROM SHESHADRIPURAM FIRST GRADE COLLEGE TO AROMA BAKERY JUNCTION VAI 3RD CROSS ROAD, 1ST A MAIN ROAD, 16TH B CROSS ROAD

CONCRETE CUBES COMPRESSIVE STRENGTH TEST REPORT

Location : Dairy circle Junction to chikkabommasandra. Junctions - RHS

Chainage : 1593 to 1980

Grade of Concrete : M30

DATE OF CASTING : 03/05/2022

DATE OF TESTING : 10/05/2022.

DATE OF TESTING : 31/05/2022.

Compressive strength test on concrete cubes specimens has been tested as per the guidelines of IS 516 /2021 Part 1 and the results are Tabulated below.

Sl.No	Quantity in 'Cum'	Samples of Cubes NO's	7 Days				28 Days				Remarks
			Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	
01	14	6	8.23	567	25.20	25.06	8.37	884	39.28	39.38	
			8.31	536	23.82		8.41	873	38.80		
			8.27	589	26.17		8.46	902	40.08		

AGENCY PMC BBMP AGENCY PMC BBMP

NCC LIMITED

WHITE TOPPING YELAHANKA FROM SHESHADRIPURAM FIRST GRADE COLLEGE TO AROMA BAKERY JUNCTION VAI 3RD CROSS ROAD, 1ST A MAIN ROAD, 16TH B CROSS ROAD

CONCRETE CUBES COMPRESSIVE STRENGTH TEST REPORT

Location : Dairy circle Junction to chikkabommasandra Junction. - RHS

Chainage : 1593 to 1980

Grade of Concrete : M30

DATE OF CASTING : 05/05/2022

DATE OF TESTING : 12/05/2022.

DATE OF TESTING : 02/06/2022.

Compressive strength test on concrete cubes specimens has been tested as per the guidelines of IS 516 /2021 Part 1 and the results are Tabulated below.

Sl.No	Quantity in 'Cum'	Samples of Cubes NO's	7 Days				28 Days				Remarks
			Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	
01	12	6	8.43	578	25.68	24.58	8.51	854	37.95	38.45	
			8.46	553	24.57		8.34	865	38.44		
			8.39	529	23.51		8.30	877	38.97		

AGENCY PMC BBMP AGENCY PMC BBMP

NCC LIMITED

WHITE TOPPING YELAHANKA FROM SHESHADRIPURAM FIRST GRADE COLLEGE TO AROMA BAKERY JUNCTION VAI 3RD CROSS ROAD, 1ST A MAIN ROAD, 16TH B CROSS ROAD

CONCRETE CUBES COMPRESSIVE STRENGTH TEST REPORT

Location : Dairy circle Junction to chikkabommasandra Junction. - RHS

Chainage : 1593 to 1980

Grade of Concrete : M30

DATE OF CASTING : 06/05/2022

DATE OF TESTING : 13/05/2022

DATE OF TESTING : 03/06/2022.

Compressive strength test on concrete cubes specimens has been tested as per the guidelines of IS 516 /2021 Part 1 and the results are Tabulated below.

Sl.No	Quantity in 'Cum'	Samples of Cubes NO's	7 Days				28 Days				Remarks
			Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	
01	12	6	8.28	544	24.17	25.03	8.46	894	39.73	38.92	
			8.33	585	26.00		8.42	832	36.97		
			8.40	561	24.93		8.32	902	40.08		

AGENCY PMC BBMP

AGENCY PMC BBMP

NCC LIMITED

WHITE TOPPING YELAHANKA FROM SHESHADRIPURAM FIRST GRADE COLLEGE TO AROMA BAKERY JUNCTION VAI 3RD CROSS ROAD, 1ST A MAIN ROAD, 16TH B CROSS ROAD

CONCRETE CUBES COMPRESSIVE STRENGTH TEST REPORT

Location : Dairy circle Junction to chikkabommasandra Junction - LHS

Chainage : 1600 to 1970

Grade of Concrete : M30

DATE OF CASTING : 09/05/2022.

DATE OF TESTING : 16/05/2022

DATE OF TESTING : 06/06/2022.

Compressive strength test on concrete cubes specimens has been tested as per the guidelines of IS 516 /2021 Part 1 and the results are Tabulated below.

Sl.No	Quantity in 'Cum'	Samples of Cubes NO's	7 Days				28 Days				Remarks
			Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	
01	15	6	8.42	598	26.57	27.10	8.37	820	36.44	37.99	
			8.48	624	27.73		8.33	866	38.48		
			8.34	608	27.02		8.43	879	39.06		

AGENCY PMC BBMP AGENCY PMC BBMP

NCC LIMITED

WHITE TOPPING YELAHANKA FROM SHESHADRIPURAM FIRST GRADE COLLEGE TO AROMA BAKERY JUNCTION VAI 3RD CROSS ROAD, 1ST A MAIN ROAD, 16TH B CROSS ROAD

CONCRETE CUBES COMPRESSIVE STRENGTH TEST REPORT

Location : Dairy circle Junction to chikkabommasandra Junction. LHS

Chainage : 1600 to 1970

Grade of Concrete : M30

DATE OF CASTING : 11/05/2022

DATE OF TESTING : 18/05/2022

DATE OF TESTING : 08/06/2022

Compressive strength test on concrete cubes specimens has been tested as per the guidelines of IS 516 /2021 Part 1 and the results are Tabulated below.

Sl.No	Quantity in 'Cum'	Samples of Cubes NO's	7 Days				28 Days				Remarks
			Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	
01	8	6	8.50	612	27.20	26.23	8.46	831	36.93	37.98	
			8.35	571	25.37		8.30	848	37.68		
			8.31	588	26.13		8.48	885	39.33		

AGENCY PMC BBMP AGENCY PMC BBMP

NCC LIMITED

WHITE TOPPING YELAHANKA FROM SHESHADRIPURAM FIRST GRADE COLLEGE TO AROMA BAKERY JUNCTION VAI 3RD CROSS ROAD, 1ST A MAIN ROAD, 16TH B CROSS ROAD

CONCRETE CUBES COMPRESSIVE STRENGTH TEST REPORT

Location : Dairy circle to chikkabommasandra Junction - LHS

Chainage : 1600 to 1970

Grade of Concrete : M30

DATE OF CASTING : 12/05/2022

DATE OF TESTING : 19/05/2022

DATE OF TESTING : 09/06/2022

Compressive strength test on concrete cubes specimens has been tested as per the guidelines of IS 516 /2021 Part 1 and the results are Tabulated below.

Sl.No	Quantity in 'Cum'	Samples of Cubes NO's	7 Days				28 Days				Remarks
			Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	
01	10	6	8.29	582	25.86	26.36	8.55	874	38.84	39.00	
			8.30	596	26.48		8.49	868	38.57		
			8.46	602	26.75		8.36	891	39.60		

AGENCY PMC BBMP AGENCY PMC BBMP

NCC LIMITED

WHITE TOPPING YELAHANKA FROM SHESHADRIPURAM FIRST GRADE COLLEGE TO AROMA BAKERY JUNCTION VAI 3RD CROSS ROAD, 1ST A MAIN ROAD, 16TH B CROSS ROAD

CONCRETE CUBES COMPRESSIVE STRENGTH TEST REPORT

Location : Daisy Circle Junction to Chikkabommasandra Junction RHS

Chainage : ch:1225 to 1980

Grade of Concrete : M20

DATE OF CASTING : 04/04/2022

DATE OF TESTING : 11/04/2022

DATE OF TESTING : 02/05/2022

Compressive strength test on concrete cubes specimens has been tested as per the guidelines of IS 516 /2021 Part 1 and the results are Tabulated below.

Sl.No	Quantity in 'Cum'	Samples of Cubes NO's	7 Days				28 Days				Remarks
			Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	
01	13	6	8.29	351	15.60	16.16	8.46	625	27.70	28.43	
			8.23	368	16.35		8.38	644	28.62		
			8.26	372	16.53		8.33	652	28.97		

AGENCY PMC BBMP AGENCY PMC BBMP

NCC LIMITED

WHITE TOPPING YELAHANKA FROM SHESHADRIPURAM FIRST GRADE COLLEGE TO AROMA BAKERY JUNCTION VAI 3RD CROSS ROAD, 1ST A MAIN ROAD, 16TH B CROSS ROAD

CONCRETE CUBES COMPRESSIVE STRENGTH TEST REPORT

Location : Dairy circle Junction to chikkabommasandra Junction - LHS

Chainage : 1100 to 1570

Grade of Concrete : M20

DATE OF CASTING : 05/04/2022.

DATE OF TESTING : 12/04/2022.

DATE OF TESTING : 03/05/2022

Compressive strength test on concrete cubes specimens has been tested as per the guidelines of IS 516 /2021 Part 1 and the results are Tabulated below.

Sl.No	Quantity in 'Cum'	Samples of Cubes NO's	7 Days				28 Days				Remarks
			Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	
01	18	6	8.19	347	15.42	16.05	8.51	618	27.46	29.06	
			8.30	354	15.73		8.40	661	29.37		
			8.32	383	17.02		8.31	683	30.35		

AGENCY PMC BBMP AGENCY PMC BBMP

NCC LIMITED

WHITE TOPPING YELAHANKA FROM SHESHADRIPURAM FIRST GRADE COLLEGE TO AROMA BAKERY JUNCTION VAI 3RD CROSS ROAD, 1ST A MAIN ROAD, 16TH B CROSS ROAD

CONCRETE CUBES COMPRESSIVE STRENGTH TEST REPORT

Location : Dairy circle Junction to chikkabommasandra Junction [Culvert Raft]

Chainage : 1108 to 1747'

Grade of Concrete : M20

DATE OF CASTING : 08/04/2022

DATE OF TESTING : 15/04/2022

DATE OF TESTING : 06/05/2022

Compressive strength test on concrete cubes specimens has been tested as per the guidelines of IS 516 /2021 Part 1 and the results are Tabulated below.

Sl.No	Quantity in 'Cum'	Samples of Cubes NO's	7 Days				28 Days				Remarks
			Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	
01	26.5	6	8.27	372	16.53	16.57	8.29	691	30.71	30.67	
			8.24	366	16.26		8.36	704	31.28		
			8.33	381	16.93		8.44	676	30.04		

AGENCY PMC BBMP AGENCY PMC BBMP

NCC LIMITED

WHITE TOPPING YELAHANKA FROM SHESHADRIPURAM FIRST GRADE COLLEGE TO AROMA BAKERY JUNCTION VAI 3RD CROSS ROAD, 1ST A MAIN ROAD, 16TH B CROSS ROAD

CONCRETE CUBES COMPRESSIVE STRENGTH TEST REPORT

Location : Kanthi Sweets to New town Bus stop RHS

Chainage : 1109 to 1980

Grade of Concrete : M20

DATE OF CASTING : 11/04/2022.

DATE OF TESTING : 18/04/2022

DATE OF TESTING : 09/05/2022

Compressive strength test on concrete cubes specimens has been tested as per the guidelines of IS 516 /2021 Part 1 and the results are Tabulated below.

Sl.No	Quantity in 'Cum'	Samples of Cubes NO's	7 Days				28 Days				Remarks
			Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	
01	7	6	8.21	340	15.11	15.85	8.25	658	29.24	30.50	
			8.32	356	15.82		8.30	711	31.60		
			8.37	374	16.62		8.43	702	31.20		

AGENCY PMC BBMP AGENCY PMC BBMP

NCC LIMITED

WHITE TOPPING YELAHANKA FROM SHESHADRIPURAM FIRST GRADE COLLEGE TO AROMA BAKERY JUNCTION VAI 3RD CROSS ROAD, 1ST A MAIN ROAD, 16TH B CROSS ROAD

CONCRETE CUBES COMPRESSIVE STRENGTH TEST REPORT

Location : Dairy circle Junction to Chikkabommasandra Junction LHS

Chainage : 1100 to 1570

Grade of Concrete : M20

DATE OF CASTING : 12/04/2022

DATE OF TESTING : 19/04/2022

DATE OF TESTING : 10/05/2022

Compressive strength test on concrete cubes specimens has been tested as per the guidelines of IS 516 /2021 Part 1 and the results are Tabulated below.

Sl.No	Quantity in 'Cum'	Samples of Cubes NO's	7 Days				28 Days				Remarks
			Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	Weight of Cubes in 'Kgs'	Crushing Load in 'KN'	Compressive Strength in 'Mpa'	Avg Compressive Strength in 'Mpa'	
01	13	6	8.41	341	15.15	15.62	8.52	622	27.64	28.29	
			8.38	350	15.55		8.46	638	28.35		
			8.44	364	16.17		8.55	650	28.88		

AGENCY PMC BBMP AGENCY PMC BBMP